

PRODUCT SPECIFICATION

IMC 312 - LOW-OXYGEN COPPER



SIZES

LOW-OXYGEN COPPER
NUGGETS & BALLS

- .56" x .5" / 14mm x 12.5mm
- .56" x .75" / 14mm x 19mm
- .75" x .75" / 19mm x 19mm
- 1" x 1" / 25mm x 25mm
- 1.375" x 1.5" / 35mm x 38mm
- 19mm / .75" (Balls)
- 25mm / 1.0" (Balls)
- 50mm / 2.0" (Balls)

PACKAGING

- 44 lb Boxes / 20 Kg
2200 lb Pallets / 1000 Kg
- 220 lb Drums / 100 Kg
1980 lb Pallets / 900 Kg
- Bulk Packaging Available

Copper ⁽¹⁾	99.95 MIN%
Iron	0.003 MAX%
Sulfur	0.003 MAX%
Lead	0.002 MAX%
Antimony	0.002 MAX%
Nickel	0.002 MAX%
Arsenic	0.001 MAX%
Tin	0.002 MAX%
Total Other ⁽²⁾	0.010 MAX%
Oxygen	0.0035 MAX%

(1) Copper includes Silver

(2) Other metallic elements include: Bi, Cd, Mn, Hg, Se, Te, Zn

FEATURES

- Hot rolling produces a fine-grained structure.
- Consistent dissolution.
- Consistent surface area.
- Quick-settling characteristics avoid bridging, voids and basket damage. (Balls)
- Perfect for automated chute loading. (Balls)
- For use in any anode basket or tray.
- Special process eliminates precleaning.
- Color-coded, user-friendly packaging.
- Certificate of Analysis issued for every lot.

TYPICAL APPLICATIONS

- Ammunition
- Coinage
- Corrosion Protection in Automotive Parts
- Decorative Plating
- Electrical Connectors
- Electronic Components
- Power Distribution Equipment
- Wire Plating

This information herein is believed to be reliable, however, no warranty, expressed or implied, is made as to its accuracy or completeness and none is made as to the fitness of this material for any purpose. The manufacturer shall not be liable to damages to person or property resulting from its use. Nothing herein shall be construed as a recommendation for use in violation of any patents.

135 Old Boiling Springs Road • Shelby, NC 28152

Phone: 704.482.8200 • Fax: 704.482.8038

www.imc-ma.com

sales@imc-ma.com